

Jacquard Acid Dye Technical Info



Jacquard Acid Dye - Primary Colors

	C	M	Y
Warm	624 Turquoise	643 Magenta	601 Yellow Sun
Cool	623 Brilliant Blue	620 Hot Fuchsia	602 Bright Yellow

Jacquard Acid Dye Properties

For wash and light fastness higher numbers are best

Color	Color Index #	Solubility in hot water g/L	Wash Fastness Scale 1-5	Light Fastness Scale 1-7	Dischargability
600 Ecu	Mix				
601 Yellow Sun	Yel 49	10	4-5	5-6	Good
602 Bright Yellow	Yel 19	20	4-5	5	Moderate
603 Golden Yellow	Mix				
604 Burnt Orange	OR 116	20	4-5	5-6	No Data
605 Pumpkin Orange	Mix	10			
606 Deep Orange	Red 111	10	20	4	Moderate
607 Salmon	Mix	30			
608 Pink	Red 418	20	4-5	5	No Data
609 Scarlet	Mix	20			
610 Burgundy	Red 299	20	3-4	5-6	Good
611 Vermillion	Mix				
612 Lilac	Mix				
613 Purple	Mix				
614 Violet	Vio 43	10	1	3	Poor
615 Periwinkle	Mix				
616 Russet	Mix				
617 Cherry Red	Red 266	10	3-4	6	Not Dischargeable
618 Fire Red	Direct Red 81	20	1-2	5	Good
619 Crimson	Mix				
620 Hot Fuchsia*	Red 52	10	3	2-3	Very Poor
621 Sky Blue	Blue 129	10	4	4-5	Poor
622 Sapphire Blue	Blue 25	10	3	5-6	Poor
623 Brilliant Blue	Blue 62	10	3-4	5-6	No Data
624 Turquoise	Blue 7	20	3	1	Moderate
625 Royal Blue	Blue 324	20	3-4	5-6	Poor
626 Navy Blue	Blue 113	40	3-4	4-5	Poor
627 Kelly Green	Mix	30-40			
628 Chartreuse*	Mix	30-40			
629 Emerald	Mix	20-30			
630 Spruce	Mix				
631 Teal	Green 25	10	4	5-6	Poor
632 Chestnut	Mix	10	3-4	4-5	Poor
633 Aztec Gold	Mix				
634 Olive	Mix				
635 Brown	Mix				
636 Gold Ochre	Mix	30-50			
637 Gun Metal	Mix	10	3-4	5	No Data
638 Silver Grey	Black 194	20	5	6-7	Not Dischargeable
639 Jet Black	Mix				
640 Fluorescent Yellow*	Yellow 7	6	4-5	2.5	Not Dischargeable
641 Fluorescent Orange*	Mix				
642 Fluorescent Red*	Mix				
643 Magenta	Red 131	20	4-5	3-4	Moderate
644 Vivid Violet**	Mix				
645 Blacklight Blue*	Mix				
646 Crocodile Green	Mix				
647 Aqua Tropic	Mix				

* = fluorecent ** = slightly fluorecent